

PRODUCT DESCRIPTION
S.I.N.: 834-300

Permatex® High Strength Threadlocker Red is a high strength anaerobic threadlocking material, which cures between engaged threads to form a unitized assembly that helps resist leakage, shock and vibration. The product is a single component, anaerobic liquid which cures when confined in the absence of air between close fitting metal surfaces. Ideal for all nut and bolt fasteners 10 mm to 25 mm in diameter where future disassembly is improbable. Excellent chemical resistance and temperature resistance range of -54°C to +149°C. Meets or exceeds the requirements of Military Specification Mil-S-46163A Type II, Grade K.

PRODUCT BENEFITS
Improved Reliability

- Eliminates vibration issues
- Seals against leakage
- Prevents rusting of threads
- Cures without cracking or shrinking

Easy Application

- No mixing
- No curing outside of joint
- No torque compensation required during assembly


TYPICAL APPLICATIONS

Prevents loosening and leakage of threaded fasteners. Particularly suitable for applications such as:


- Cylinder block
- Rocker arm studs
- Ring gear bolts
- Frame bolts
- Frame brackets
- Hydraulic press studs

DIRECTIONS FOR USE
For Assembly

1. Clean all threads (Bolt and Hole) with a cleaning solvent such as Brake and Parts Cleaner and allow to dry
2. Determine if the threads to be bonded are Active or Inactive Metals (Ref: Cure Speed vs. Substrate on the second page). If material is an Inactive Metal, spray all threads with Surface Prep and allow 30 seconds to dry. Priming is not required if the material is an Active Metal. If unknown, it is always best to use the activator.
3. Shake the product thoroughly before use
4. To prevent the product from clogging in the nozzle, do not allow the tip to touch metal surfaces during application.
5. For Thru Holes, apply several drops of product onto the bolt at the nut engagement area.



1. For Blind Holes, apply several drops down the female threads into the bottom of the hole. As threads are engaged, compressed air forces the product upwards into the threads.



2. Assemble and tighten as usual. When tightening to established torque values, torque compensation is not required.

For Clean-up

1. Residual liquid films and/or fillets outside the joint are readily soluble in Brake and Parts Cleaner
2. Cured product can be removed with a combination of soaking in Gasket Remover and mechanical abrasion such as a wire brush.

For Disassembly

1. Apply localized heat to nut or bolt to approximately 232 °C. Disassemble while hot.

For Reassembly

1. Remove loose product from nut and bolt
2. Apply activator to all threads, regardless of metal type
3. Assemble and tighten as usual.

PROPERTIES OF UNCURED MATERIAL

	Typical value
Chemical Type	Anaerobic Dimethacrylate Ester
Appearance	Opaque Red Fluorescent Liquid
Specific Gravity @ 27 °C	1.10
Viscosity @ 25 °C, mPas (cP) BrookField RVF, spindle #3 @ 20 RPM	400 to 600
Flash Point (TCC), °C	>93


TYPICAL CURING PERFORMANCE

Cure speed vs. substrate

The rate of cure will depend on the material used. Permatex® High Strength Threadlocker Red will react faster and stronger with **Active Metals**. However, **Inactive Metals** will require the use of an activator (Surface Prep) to obtain maximum strength and cure speed at room temperature.

Active Metals	Inactive Metals
Soft Steel Iron	Bright Platings
Copper	Anodized Surfaces
Brass	Titanium
Manganese	Zinc
Bronze	Pure Aluminum
Nickel	Stainless Steel
Aluminum Alloy	Cadmium

The graph below shows the breakaway strength developed with time on 3/8" - 16 Grade 5 bolts and Grade 8 nuts compared to different materials.




Cure speed vs. temperature

The rate of cure will depend on the ambient temperature. Full cure is attainable in 24 hours at room temperature, 22 °C, or 1 hour at 93 °C.

Cure speed vs. activator

Where cure speed is unacceptably long, or large gaps are present, applying an activator (Surface Prep) to the surface will improve cure speed. A 3/8-16 steel nut and bolt assembly will fixture in about 5 minutes using an activator, while fixturing will occur in about 20 minutes without an activator. Full cure in 24 hours for both procedures. The graph below shows the breakaway strength developed with time using Surface Prep Activator.

PERFORMANCE OF CURED MATERIAL



(After 24 hr at 22 °C on degreased 3/8-16 steel Grade 8 nuts and Grade 5 bolts)

	Typical Value	Range
Breakaway Torque, Nm	28	17 to 40
Prevail Torque, Nm	31	23 to 40

Where Breakaway Torque is the force required to initiate the fastener movement and Prevail Torque is the force required to disassemble the fastener once Breakaway Torque has occurred.

TYPICAL ENVIRONMENTAL RESISTANCE

Temperature Resistance

Product temperature range from -54°C to +149°C. The breakaway and prevailing torque values decrease as temperature increases; however the assembly remains effective against vibration and leakage.

Chemical / Solvent Resistance

Aged under conditions and tested at 22°C

% Initial Strength retained after time	Temp	500hr	1000hr
Hot air	150 °C		56%
Motor oil (SL)	125 °C		48%
Gasoline	23 °C	98%	
Antifreeze	87 °C	85%	
Ethanol	23 °C	105%	
Acetone	23 °C	102%	

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials. For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

This product is not normally recommended for use on plastics (particularly thermoplastic materials where stress cracking of the plastic could result). It is recommended to confirm compatibility of the product with such substrates.

STORAGE

Products shall be ideally stored in a cool, dry location in unopened containers at a temperature between 8°C to 28°C unless otherwise labelled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused product, do not return any material to its original container.

NOTE

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. **Permatex Europe specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Permatex Europe products and disclaims any liability for consequential or incidental damages of any kind, including lost profits.** This product may be covered by one or more United States or foreign patents or patent applications.

Part Number	Container Size
27111, 27112	10ml Bottle, Carded
35375, 27152	50ml Bottle